



# CEWELD AA NiFe36

TYPE	Flux cored welding wire developed for welding cast iron with excellent weldability.										
ANWENDUNGEN	Joining and rebuilding Cast Iron with globular graphite, tempered Cast Iron and for joining Cast Iron with steel. Used for standards of length, measuring devices, laser components, bi-metal thermostat strip, thermostat rods, and tanks and piping for storing and transporting liquefied gases.										
EIGENSCHAFTEN	Very good welding and wetting characteristics and high resistance to cracks and fissures. Extreme good deposition rate compare to MMA. High strength and good bonding weld metal. NiFe36 has a composition that matches "NiLo" and offer the lowest shrinkage possible to avoid cracks during heating and the cooling period. The weld deposit also retains good strength and toughness at cryogenic temperatures and has a low coefficient of expansion from cryogenic temperatures to about 500°F (260°C).										
KLASSIFIKATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.15: E NiFe-CI</td> </tr> <tr> <td>EN ISO</td> <td>1071: T C NiFe-1</td> </tr> <tr> <td>W.Nr.</td> <td>1.3912</td> </tr> </table>	AWS	A 5.15: E NiFe-CI	EN ISO	1071: T C NiFe-1	W.Nr.	1.3912				
AWS	A 5.15: E NiFe-CI										
EN ISO	1071: T C NiFe-1										
W.Nr.	1.3912										
GEEIGNET FÜR	<p>Spheroidal Cast Iron, Diluted Cast Iron, old Cast Iron, Steel to Cast Iron etc.</p> <p><b>EN 1561:</b> EN-GJL-100, EN-GJL-150, EN-GJL-200, EN-GJL-250, EN-GJL-300, EN-GJL-350, GG10, GG15; GG20, GG25; GG30; GG35; GG40</p> <p><b>EN 1562:</b> EN-GJMB-350, EN-GJMB-550 , EN- GJMW-350, EN- GJMW-550 , GTS 35, GTS 55, GTW 35, GTW 55</p> <p><b>EN1563:</b> EN-GJS-400-15, EN-GJS-400-18, EN-GJS-450-10, EN-GJS-500-7, EN-GJS-600-3, EN-GJS-700-2. GGG40, GGG45, GGG50, GGG60; GGG70, GGG80</p>										
ZULASSUNGEN											
SCHWEISSPOSITIONEN											
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>Ni</th> <th>Fe</th> </tr> </thead> <tbody> <tr> <td>0.1</td> <td>0.5</td> <td>2.4</td> <td>36</td> <td>Rem.</td> </tr> </tbody> </table>	C	Si	Mn	Ni	Fe	0.1	0.5	2.4	36	Rem.
C	Si	Mn	Ni	Fe							
0.1	0.5	2.4	36	Rem.							
MECHANISCHE GÜTEWERTE	<table border="1"> <thead> <tr> <th>Heat Treatment</th> <th>R<sub>P0,2</sub> (MPa)</th> <th>R<sub>m</sub> (MPa)</th> <th>A<sub>5</sub> (%)</th> <th>Hardness</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td></td> <td></td> <td></td> <td>150 HV</td> </tr> </tbody> </table>	Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness	As Welded				150 HV
Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness							
As Welded				150 HV							
RÜCKTROCKNUNG	Not required										
GAS ACC. EN ISO 14175	I1, M13										