



CEWELD Alu-Flux

| | |
|-----------------------|---|
| TYPE | Flux for aluminium brazing |
| ANWENDUNGEN | Alu-Fux is for brazing from Aluminium and Aluminium Alloys with a working range from 350 to 550 °C |
| EIGENSCHAFTEN | Usually combined with AlSi12 or AlSi5 filler metal. |
| KLASSIFIKATION | EN ISO 18496: FL20 |
| GEEIGNET FÜR | Brazing for Aluminium and Aluminium Alloys with a working range from 350 to 550 °C. Usually combined with AlSi12 or AlSi5 filler metal. |
| ZULASSUNGEN | |
| SCHWEISSPOSITIONEN | |
| (%) | |
| MECHANISCHE GÜTEWERTE | |
| RÜCKTROCKNUNG | Not required |
| GAS ACC. EN ISO 14175 | |



CEWELD Alu-Flux

ALU-FLUX NAMM

| Packaging | KG/unit | EanCode |
|-----------|---------|---------------|
| Jar | 0,25 | 8720663423016 |