

CEWELD E DUR 400 CrMo

TYPE Basic coated electrode for rebuilding heat resistant machine parts and buffer layers.

ANWENDUNGEN Hardfacing, rebuilding, overlays, machine parts, wheels, conveyors, crossings, buffer layers prior to Hardfacing etc.


EIGENSCHAFTEN Outstanding alloy against high impact combined with abrasion including metal to metal friction and increased working temperatures up to 550 °C. Due to the high resistance to cracking and toughness, all weld metal requires no buffer layer except on materials considered critical. Suited for wear parts subject to heavy impact and shock. The weld metal is machinable with carbide tip tools, hardening is possible. The maximum hardness is dependent on the base metal and is often achieved in the first layer.

KLASSIFIKATION EN ISO 14700: E Fe3
DIN 8555: E 3-UM-40-PT

GEEIGNET FÜR Rebuilding worn machine parts, Stone crushers, Hammers, Gears, Cams, rails, crossings etc.

ZULASSUNGEN

SCHWEISSPOSITIONEN



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)


C	Mn	Cr	Mo	Fe	Si
0.1	0.6	6.5	3	Rem.	0.4

MECHANISCHE GÜTEWERTE

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded				40 HRc

RÜCKTROCKNUNG 300°C / 2 hr

GAS ACC. EN ISO 14175



CEWELD E DUR 400 CrMo

E DUR 400 CRMO 2,5 X
350MM

Packaging	KG/unit	EanCode
Can	3	8720663401601