



CEWELD NiCr 52 Tig

TYPE	Solid nickel base welding wire for Tungsten Inert Gas (Tig) welding.																									
ANWENDUNGEN	CEWELD Nicro 52 filler metal is used for welding nickel-chromium-iron (Inconel 690) alloys to themselves, and for dissimilar welding between nickel-chromium-iron alloys and steels or stainless steels. The applications include surfacing as well as clad-side welding. Interpass temperature of 150°C should be respected,																									
EIGENSCHAFTEN	Excellent resistance against oxidizing media combined with high mechanical strength at room temperature but also at extreme high temperatures combined with high ductility due to the high chromium content. Alloy 690 was developed to offer greater resistance to stress corrosion in the nuclear industry, pure water environment..																									
KLASSIFIKATION	AWS	A 5.14: ERNiCrFe-7																								
	EN ISO	18274: S Ni 6052(NiCr30Fe9)																								
	W.Nr.	2.4642																								
	F-nr	43																								
	FM	6																								
GEEIGNET FÜR	Inconel 690, VDM Alloy 690, Nicrofer 6030 N, FM 52, 2.4642, NiCr29Fe																									
ZULASSUNGEN																										
SCHWEISSPOSITIONEN																										
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Ti</th> <th>Fe</th> <th>Al</th> </tr> </thead> <tbody> <tr> <td>0.02</td> <td>0.4</td> <td>0.8</td> <td>30</td> <td>60</td> <td>0.2</td> <td>0.5</td> <td>10</td> <td>0.3</td> </tr> </tbody> </table>								C	Si	Mn	Cr	Ni	Mo	Ti	Fe	Al	0.02	0.4	0.8	30	60	0.2	0.5	10	0.3
C	Si	Mn	Cr	Ni	Mo	Ti	Fe	Al																		
0.02	0.4	0.8	30	60	0.2	0.5	10	0.3																		
MECHANISCHE GÜTEWERTE	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>Heat Treatment</th> <th>R_{P0,2} (MPa)</th> <th>R_m (MPa)</th> <th>A₅ (%)</th> <th>Hardness</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>770</td> <td>870</td> <td>16</td> <td>HRc</td> </tr> <tr> <td>580°C±15°C 1h</td> <td>260</td> <td>580</td> <td>30</td> <td>200 HB</td> </tr> </tbody> </table>		Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness	As Welded	770	870	16	HRc	580°C±15°C 1h	260	580	30	200 HB									
Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness																						
As Welded	770	870	16	HRc																						
580°C±15°C 1h	260	580	30	200 HB																						
RÜCKTROCKNUNG	Not required																									
GAS ACC. EN ISO 14175	I1																									



CEWELD NiCro 52 Tig

NICRO 52 TIG 1,6 X 914MM

Packaging	KG/unit	EanCode
Tube	4,54	8720663418241

NICRO 52 TIG 2,4 X 1000MM

Packaging	KG/unit	EanCode
Tube	4,54	8720663418265