



# CEWELD AA R Corten

TYPE	Seamless micro-alloyed rutile flux-cored wire for M21.																					
ANWENDUNGEN	Weather resistant steels, cranes, equipment, vessel and construction.																					
EIGENSCHAFTEN	Excellent weld puddle manipulation with fast freezing slag, superior out-of-position welding also at higher currents. Using temperature down to - 40 °C. Particularly suited for MAG-orbital welding and all-position welding on ceramic backing. Extreme low spatter loss, easy slag removal and hydrogen content below 3 ml/100gr. even after long unconditioned storage.																					
KLASSIFIKATION	AWS A 5.29: E81T1-G H4 EN ISO 17632-A: T 46 5 Z P M21 H5 F-nr 6 FM 1																					
GEEIGNET FÜR	<b>CuNi, Reh ≤ 460MPa ISo 15608: 1.4</b> 1.8963, 1.8946, 1.8965 S235JRG2Cu, S235J2G4Cu, S235J0Cu, S235JRW, S355J0Cu, S355J2G3Cu, S355J0W, 235J2W- S355J2W, S355K2W, WTSt 37, WTSt 52, ASTM A 588M Grade A,B, C...K, A 618 Gr. II; A 709 Gr. 50 WF3 CORten A, B, C, Patinax 37																					
ZULASSUNGEN	CE																					
SCHWEISSPOSITIONEN																						
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table><tr><td>C</td><td>Si</td><td>Mn</td><td>P</td><td>S</td><td>Cr</td><td>Ni</td><td>Cu</td></tr><tr><td>0.05</td><td>0.7</td><td>1.5</td><td>0.015</td><td>0.015</td><td>0.5</td><td>1.2</td><td>0.5</td></tr></table>	C	Si	Mn	P	S	Cr	Ni	Cu	0.05	0.7	1.5	0.015	0.015	0.5	1.2	0.5					
C	Si	Mn	P	S	Cr	Ni	Cu															
0.05	0.7	1.5	0.015	0.015	0.5	1.2	0.5															
MECHANISCHE GÜTEWERTE	<table><thead><tr><th>Heat Treatment</th><th>R<sub>P0,2</sub> (MPa)</th><th>R<sub>m</sub> (MPa)</th><th>A5 (%)</th><th colspan="2">Impact Energy (J) ISO-V</th><th>Hardness</th></tr><tr><th colspan="4"></th><th colspan="2">-50°C</th><th></th></tr></thead><tbody><tr><td>As Welded</td><td>510</td><td>620</td><td>22</td><td colspan="2">55</td><td>HRc</td></tr></tbody></table>	Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A5 (%)	Impact Energy (J) ISO-V		Hardness					-50°C			As Welded	510	620	22	55		HRc
Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A5 (%)	Impact Energy (J) ISO-V		Hardness																
				-50°C																		
As Welded	510	620	22	55		HRc																
RÜCKTROCKNUNG	Not required																					
GAS ACC. EN ISO 14175	M21																					



# CEWELD AA R Corten

AA R CORTEN 1,2MM

Packaging	KG/unit	EanCode
BS-300	16	8720663405401