



CEWELD AA NiCrO 600B

TYPE	Basic flux-cored nickel base welding wire for gas shielded arc welding.																
ANWENDUNGEN	AA NICRO 600B is developed for welding and cladding nickel-based alloys such as alloy 600 or similar materials. This alloy can also be used for welding dissimilar nickel-based alloys to each other, to alloyed steels or to stainless steels. AA NICRO 600B can also be used on difficult to weld steels !																
EIGENSCHAFTEN	Latest generation basic slag quality guarantees optimum metallurgical quality and attractive welder appeal. The weld deposit meets the NiCrFe-3 requirements. Better bead aspect and shape compare to solid wires with better arc stability and improved wetting properties with less spatters. Excellent results are also achieved without protective gas.																
KLASSIFIKATION	<table border="0"> <tr> <td>EN ISO</td> <td>12153-A: T Ni 6082 (NiCr15Fe6Mn) R M21 3</td> </tr> <tr> <td>W.Nr.</td> <td>2.4648</td> </tr> <tr> <td>F-nr</td> <td>43</td> </tr> <tr> <td>FM</td> <td>6</td> </tr> </table>	EN ISO	12153-A: T Ni 6082 (NiCr15Fe6Mn) R M21 3	W.Nr.	2.4648	F-nr	43	FM	6								
EN ISO	12153-A: T Ni 6082 (NiCr15Fe6Mn) R M21 3																
W.Nr.	2.4648																
F-nr	43																
FM	6																
GEEIGNET FÜR	<p>E NiCr3 / Ni6082 / NiCr15Fe6Mn 1.4816, 1.4864, 1.4876, 1.4583, 1.4886, 1.5637, 1.5662, 1.5680, 1.6900, 1.6901, 1.6903, 1.6906, 2.4630, 2.4631, 2.4669, 2.4816, 2.4817, 2.4851, 2.4867, 2.4870, 2.4951 NiCr20Ti, NiCr21TiAl, NiCr15Fe7TiAl, NiCr15Fe, LC-NiCr15Fe, NiCr23Fe, NiCr60 15, NiCr80 20, NiCr 10, NiCr20Ti 1.5637 12 Ni 14, X8Ni9, 12Ni19, X12CrNi18 9, GX8CrNi18 10, X10CrNi18 10, X5CrNi18 10 UNS Nr: K81340 - N06600 - N06601 - N08800 - N08810 Alloy 600, Alloy 600 L, Alloy 800 / 800H UNS N06600, N07080, N0800, N0810</p>																
ZULASSUNGEN																	
SCHWEISSPOSITIONEN																	
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>Cr</th> <th>Ni</th> <th>Nb</th> <th>Fe</th> <th>S</th> </tr> </thead> <tbody> <tr> <td>0.01</td> <td>0.3</td> <td>5</td> <td>16.5</td> <td>Rem.</td> <td>1.7</td> <td>6</td> <td>0.015</td> </tr> </tbody> </table>	C	Si	Mn	Cr	Ni	Nb	Fe	S	0.01	0.3	5	16.5	Rem.	1.7	6	0.015
C	Si	Mn	Cr	Ni	Nb	Fe	S										
0.01	0.3	5	16.5	Rem.	1.7	6	0.015										
MECHANISCHE GÜTEWERTE	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0.2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th colspan="2">-196°C</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>390</td> <td>610</td> <td>45</td> <td colspan="2">90</td> <td>HRC</td> </tr> </tbody> </table>	Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	-196°C		As Welded	390	610	45	90		HRC
Heat Treatment	R _{P0.2} (MPa)					R _m (MPa)	A ₅ (%)		Impact Energy (J) ISO-V		Hardness						
		-196°C															
As Welded	390	610	45	90		HRC											
RÜCKTROCKNUNG	140°C / 24 hr																
GAS ACC. EN ISO 14175	M21																