





TYPE Fluxcored hardfacing welding wire with Nickel matrix and 60% Tungsten carbides (WC2)

APPLICATIONS This Ni-based alloy provides an excellent corrosion resistance combined with extreme abrasion

resistance. OA WC2 (Ni) can be applied on all sorts of steels except on cast iron or Mn-steel. This alloy is the most wear resistant type in most hardfacing applications. In case of very fine dust abrasion It might happen that the matrix will be washed out and looses the imbedded Tungsten

carbides, in this case another hardfacing product should be considdered.

PROPERTIES 2400 HV nickel based corrosion resistant hardfacing alloy containing 60% tunsten carbides. OA WC2

(Ni) has excellent flow and wetting characteristics. Multi-layer deposits are possible and worn parts can be rebuild without removing the old material. Crushed cast carbide will guaranty a long life for several wear applications. Best to be used with shielding gas M13 (Argon with 1% Oxygen)

approx. 15 litres per minute.

CLASSIFICATION EN ISO 14700: T Ni20

DIN 8555: MF 21-GF-55-CGTZ

SUITABLE FOR Rebuilding of stabilisers and other oilfield tools where maximum protection is required. Also for

augers, impellers, mixer plates in the brick and clay industry and on decanter screws or hardfacing

deep drilling equipment.

APPROVALS

WELDING POSITIONS



TYPICAL CHEMICAL

ANALYSIS OF WELD METAL

ANALYSIS OF WELD METAL (%)

С	Si	Ni	TFC	Cr	В
0.4	2.5	Rem.	44	2.7	1.7

MECHANICAL PROPERTIES

Heat	R _{P0,2}	Rm	A5	Hardness
Treatment	(MPa)	(MPa)	(%)	
As Welded				2400 HV

REDRYING 140°C / 24 hr

GAS ACC. EN ISO 14175





CEWELD OA WC2 Ni

OA WC2 NI 1,2MM	Packaging	KG/unit	EanCode	
	BS-300	15	8720663403865	
OA WC2 NI 1,6MM	Packaging	KG/unit	EanCode	
	BS-300	15	8720663403889	
OA WC2 NI 2,4MM	Packaging	KG/unit	EanCode	
	BS-300	15	8720663403902	