



CEWELD AA DUR 6

TYPE	Cobalt based (Stellite 6) fluxcored welding wire (FCAW) for overlay welding.									
APPLICATIONS	Cladding valves, Steam-valves, high temperature liquid pumps, hot cutting tools, exhaust valves, seats, cutting knives, metal to metal wear, bearing surfaces, chemical industry, hot shear blades etc. Cladding valves, Steam-valves, high temperature liquid pumps, hot cutting tools, exhaust valves, seats, cutting knives, metal to metal wear, bearing surfaces, chemical industry, hot shear blades etc.									
PROPERTIES	Outstanding alloy against abrasion, thermo-shock and corrosion combined with high temperatures. The weld deposit can be machined with tungsten tool tips and by grinding. The hardness of the weld deposit will degrease 16% at 300°C and about 30% at 600°C. Excellent alloy against thermal shock, abrasion, erosion, corrosion and cavitation at high temperature.									
CLASSIFICATION	AWS EN ISO DIN F-nr	EN ISO 14700: T Co2 DIN 8555: MSG 20-GF-40-CTZ								
SUITABLE FOR	ER CoCr-A Stellite 6 Celist 706									
APPROVALS										
WELDING POSITIONS	PA PB PC									
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	С	Si	Mn	Cr	Ni	Mo	F	e	W	Co
	1	1	0.8	28	2	0.01		3	4.5	Rem.
MECHANICAL PROPERTIES	Heat Treatment As Welded			R _{P0,2} (MPa)		Rm (MPa)		Hardnes		SS
									43 HRc	
REDRYING	140°C / 24	hr								
GAS ACC. EN ISO 14175	M13									





CEWELD AA DUR 6

AA DUR 6 0,8MM	Packaging	KG/unit	EanCode				
	BS-300	15	8720663402011				
AA DUR 6 1,2MM	Packaging	KG/unit	EanCode				
	BS-300	15	8720663402028				
AA DUR 6 1,6MM	Packaging	KG/unit	EanCode				
	BS-300	15	8720663402042				