


CEWELD E DUR MnCr

TYPE	Basic Hardfacing electrode with high impact and wear resistance								
APPLICATIONS	Basic electrode for rebuilding and joining cold straining Mn steels or rebuilding parts that are subject to high impact and rolling wear.								
PROPERTIES	There is no limit for the number of layers that can be applied in case of rebuilding but heat input should be kept low (as for Mn steel, interpass temperature should be kept < 250 °C).								
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.13: E FeMnCr</td> </tr> <tr> <td>EN ISO</td> <td>14700: E Fe9</td> </tr> <tr> <td>DIN</td> <td>8555: E 7-UM-250-K</td> </tr> <tr> <td>F-nr</td> <td>71</td> </tr> </table>	AWS	A 5.13: E FeMnCr	EN ISO	14700: E Fe9	DIN	8555: E 7-UM-250-K	F-nr	71
AWS	A 5.13: E FeMnCr								
EN ISO	14700: E Fe9								
DIN	8555: E 7-UM-250-K								
F-nr	71								
SUITABLE FOR	Rebuilding and joining cold straining Mn steels or rebuilding parts that are subject to high impact and rolling wear. Breaker teeth, Crushers, Hammers, Crossings, Rails.								

APPROVALS

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

C	Mn	Cr	Fe	Si
0.75	17.5	14	Rem.	0.4

MECHANICAL PROPERTIES

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded				270 HB

REDRYING 300°C / 2 hr

GAS ACC. EN ISO 14175



CEWELD E DUR MnCr

E DUR MNCR 2,5 X 350MM	Packaging	KG/unit	EanCode
	Can	2,5	8720663401496
E DUR MNCR 3,2 X 350MM	Packaging	KG/unit	EanCode
	Can	2,5	8720663401502
E DUR MNCR 4,0 X 450MM	Packaging	KG/unit	EanCode
	Can	3,0	8720663401519