


CEWELD CroNi 29-9 HLS

TYPE	Special alloy for welding unknown and difficult to weld steels.(Type 312, 29 9 , 1.4337)																
APPLICATIONS	CroNi 29/9 HLS is a austenitic-ferritic special alloy high recovery rutile electrode suitable for joining steels that are difficult to weld. Varied applications in repair and maintenance of machines, shafts, gearwheels, especially in the field of construction machinery. Also excellent for buffer layers before Hardfacing and for dissimilar welding between steel, stainless steels or unknown steels.																
PROPERTIES	Very popular because of its soft, stable arc, its easy spatter free application and the very good slag removal with no residues. High corrosion resistance and high temperature resistance up to 1100 °C. with excellent weldability on both AC and DC+.																
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.4: E 312-26</td> </tr> <tr> <td>EN ISO</td> <td>3581-A: E 29 9 R 53</td> </tr> <tr> <td>W.Nr.</td> <td>1.4337</td> </tr> <tr> <td>F-nr</td> <td>5</td> </tr> <tr> <td>FM</td> <td>5</td> </tr> </table>	AWS	A 5.4: E 312-26	EN ISO	3581-A: E 29 9 R 53	W.Nr.	1.4337	F-nr	5	FM	5						
AWS	A 5.4: E 312-26																
EN ISO	3581-A: E 29 9 R 53																
W.Nr.	1.4337																
F-nr	5																
FM	5																
SUITABLE FOR	<p>ISO 15608: 11 (0,25 % < C ≤ 0,85 %) Type: 29% Cr, 9%Ni 1.3401, 1.4006, 1.4339, 1.4340, 1.4347, 1.4460 X120Mn12, X10Cr13, GX32CrNi28-10, GX49CrNi27-4, GX8CrCrNiN26-7, X3CrNiMoN27-5-2 UNS S41000 AISI 329, 410, S235, E295 Hss, C45, C60, dissimilar welding, maintenance, buffer layers, repairing cock wheels, 42MnV7, 25CrMo4, 42CrMo4, 50CrMo4, 1.5223, 1.7218, 1.7225, 1.7228, ArmoX, Hardox</p>																
APPROVALS	CE																
WELDING POSITIONS																	
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> </tr> </thead> <tbody> <tr> <td>0.1</td> <td>0.8</td> <td>2</td> <td>0.025</td> <td>0.015</td> <td>30</td> <td>9.5</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Cr	Ni	0.1	0.8	2	0.025	0.015	30	9.5		
C	Si	Mn	P	S	Cr	Ni											
0.1	0.8	2	0.025	0.015	30	9.5											
MECHANICAL PROPERTIES	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0,2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th colspan="2">RT</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>500</td> <td>750</td> <td>23</td> <td colspan="2">40</td> <td>300 HB</td> </tr> </tbody> </table>	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	RT		As Welded	500	750	23	40		300 HB
Heat Treatment	R _{P0,2} (MPa)					R _m (MPa)	A ₅ (%)		Impact Energy (J) ISO-V		Hardness						
		RT															
As Welded	500	750	23	40		300 HB											
REDRYING	Not required																
GAS ACC. EN ISO 14175																	