



# CEWELD AA 309LMoP

TYPE	Stainless steel Rutile flux cored weldig wire. ( Typ 309LMo, 23 12 2 L, 1.4459)										
APPLICATIONS	CEWELD AA 309LMoP you can use for cladding applications in case a AISI 316 is required in the first layer, suitable for dissimilar welding of steel to stainless steel, heat resistant up to 1050 degrees Celsius										
PROPERTIES	CEWELD AA 309LMoP is a flux cored wire with rapidly solidifying slag (P in Standard) support for high productivity welding in all positions. Excellent for use on ceramic backing strips. The slag is self detaching and offers extra protection to obtain X-ray proof weld seams with practically no spatters. Better wetting and welding properties with more productivity compared to solid wires.										
CLASSIFICATION	AWS	A 5.22: E309LMoT1-4									
	EN ISO	17633-A: T 23 12 2 L P M21 1									
	W.Nr.	1.4459									
	F-nr	6									
	FM	5									
SUITABLE FOR	<b>ISO 15608: 8.1 Austenitic ≤ 19 % Cr , TÜV 1000: Gr. 21-30,</b> 1.4583, 1.4435, 1.4436, 1.4404, 1.4406, 1.4408, 1.4401, 1.4571, 1.4580, 1.4406, 1.4521, 1.4301, 1.4306, X102CrNiMoNb 18 12, X2CrNiMo 18 14 3 (TP), X4CrNiMo 17 13 3, X2CrNiMo 17 12 2 (TP), X 5CrNiMo 19 11 2, X4CrNiMo 17 12 2 (TP), X6CrNiMo 17 12 2, X6CrNiMoNb 17 12 3, X2CrNiMoN 17 12 3 (TP), X2CrMoTi18-2 316Cb, 316L, 316L, 316LN, 316H, 316, 316Ti, 316Cb, 316LN, 444 S31640, S31603, S31653, S31600, S31630, S44400										
APPROVALS	CE										
WELDING POSITIONS											
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	P	Cr	Ni	Mo	S	FN	FS	FNW
	0.025	0.55	0.9	0.015	23	12.5	2.5	0.015	18	17	25
MECHANICAL PROPERTIES	Heat Treatment	R <sub>P0.2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Impact Energy (J) ISO-V				Hardness		
	As Welded	400	600	32	RT		-40°C		HRc		
					110		27				
REDRYING	140°C / 24 hr										
GAS ACC. EN ISO 14175	M21, C1										



# CEWELD AA 309LMoP

AA 309LMOP 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663413796
D-200	5	8720663413802