



CEWELD Alu-Flux

TYPE	Flux for aluminium brazing
APPLICATIONS	Alu-Fux is for brazing from Aluminium and Aluminium Alloys with a working range from 350 to 550 °C
PROPRIÉTÉS	Usually combined with AlSi12 or AlSi5 filler metal.
CLASSIFICATION	EN ISO 18496: FL20
CONVIENT POUR	Brazing for Aluminium and Aluminium Alloys with a working range from 350 to 550 °C. Usually combined with AlSi12 or AlSi5 filler metal.
AGRÉMENTS	
POSITIONS DE SOUDAGE	
(%)	
PROPRIÉTÉS MÉCANIQUES	
ETUVAGE	Not required
GAS ACC. EN ISO 14175	



CEWELD Alu-Flux

ALU-FLUX NAMM

Packaging	KG/unit	EanCode
Jar	0,25	8720663423016