



# CEWELD NiFe 55

TYPE	Nickel iron MIG wire for joining dissimilar materials and cast iron.																
TOEPASSINGEN	Suitable for welding stainless steels containing 12-14 Cr. Also for welding mild and low alloy steels which are exposed to temperatures up to 450C. Cast Iron repairs, rebuilding shafts, wheels, critical joints between steel and cast iron etc.																
EIGENSCHAPPEN	Nickel Iron based filler metal for joint welding and claddings on cast Iron. Very well suited also for dissimilar welding between cast iron and high alloyed stainless and heat resistant steels or mild steels. Excellent Weldability with extreme crack resistance with a ductile weld deposit. Good welding and wetting characteristics and high resistance against porosity. The weld metal is corrosion and heat resistant. Very well suitable for welding with robotics or automated processes.																
CLASSIFICATIE	<table border="0"> <tr> <td>AWS</td> <td>A 5.15: E NiFe-CI</td> </tr> <tr> <td>EN ISO</td> <td>1071: SC NiFe-1</td> </tr> <tr> <td>W.Nr.</td> <td>2.4472</td> </tr> </table>	AWS	A 5.15: E NiFe-CI	EN ISO	1071: SC NiFe-1	W.Nr.	2.4472										
AWS	A 5.15: E NiFe-CI																
EN ISO	1071: SC NiFe-1																
W.Nr.	2.4472																
GESCHIKT VOOR	Grey cast iron, malleable, nodular : NF A 32-101 : FGL 150, 200, 250, 300, 350, 400. NF A 32-201 : FGS 370-17, 400-12, 500-7, 600-3, 700-2. NF A 32-702 : MN 350-10, 380-18, 450-6, 350-4, 650-3. DIN 1691 : CG-14, 18, 25, 30. DIN 1693 : GGG-40, 50, 60, 70. DIN 1692 : GTS-35, 45, 55, 65, 70.																
GOEDKEURINGEN																	
LASPOSITIES																	
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Ni</th> <th>Fe</th> <th>Cu</th> </tr> </thead> <tbody> <tr> <td>0.015</td> <td>0.06</td> <td>0.65</td> <td>0.003</td> <td>0.001</td> <td>55</td> <td>Rem.</td> <td>0.01</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Ni	Fe	Cu	0.015	0.06	0.65	0.003	0.001	55	Rem.	0.01
C	Si	Mn	P	S	Ni	Fe	Cu										
0.015	0.06	0.65	0.003	0.001	55	Rem.	0.01										
MECHANISCHE WAARDEN	<table border="1"> <thead> <tr> <th>Heat Treatment</th> <th>R<sub>P0.2</sub> (MPa)</th> <th>R<sub>m</sub> (MPa)</th> <th>A<sub>5</sub> (%)</th> <th>Hardness</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>350</td> <td>480</td> <td>12</td> <td>195 HB</td> </tr> </tbody> </table>	Heat Treatment	R <sub>P0.2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness	As Welded	350	480	12	195 HB						
Heat Treatment	R <sub>P0.2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness													
As Welded	350	480	12	195 HB													
HERDROGEN	Not required																
GAS ACC. EN ISO 14175	I1																