



CEWELD E DUR 350 Kb

TYPE Basic coated electrode for hardfacing machine parts, buffer layers and rebuilding rails and crossings..

TOEPASSINGEN Hardfacing and rebuilding machine parts that faces high impact and wear. The alloy is also excellent for buffer layers prior to Hardfacing.


EIGENSCHAPPEN CEWELD® E DUR 350 Kb is a Hardfacing electrode against high impact combined with abrasion. This alloy has no risk for cracks and can also be applied on austenitic manganese steels. The weld deposit is good machinable. Very good weld deposit appearance and outstanding welding properties on both AC and DC+. Preheating is not required. Outstanding slag release.

CLASSIFICATIE EN ISO 14700: E Fe1
DIN 8555: E 1-UM-350-P

GESCHIKT VOOR Rebuilding worn machine parts such as, Rails, Crossings, Wheels, Dredging parts, Stone crushers, Hammers, Gears, Cams, Bearings, Rope winches etc.

GOEDKEURINGEN

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

| C | Mn | Ni | Fe | Si |
|------|-----|----|------|-----|
| 0.15 | 1.1 | 3 | Rem. | 0.7 |

MECHANISCHE WAARDEN

| Heat Treatment | R _{P0,2} (MPa) | R _m (MPa) | A ₅ (%) | Hardness |
|----------------|-------------------------|----------------------|--------------------|----------|
| As Welded | | | | 370 HB |

HERDROGEN 140°C / 2 hr

GAS ACC. EN ISO 14175