



CEWELD SA 316L

TYPE	Solid stainless steel welding wire for submerged arc welding																							
TOEPASSINGEN	The alloy is widely used in the chemical and food-processing industries, as well as in shipbuilding, vessel and various types of architectural structure. Suitable for welding corrosion-resistant Cr-Ni-Mo steels with extremely low C-content at working temperatures up to 350°C.																							
EIGENSCHAPPEN	SA 316L offers good general corrosion resistance, particularly to corrosion in acid and chlorinated environments. The alloy has a low carbon content which makes it particularly recommended when there is a risk of intergranular corrosion. can be used with our fused flux FL 880 or agglomerated fluxes FL 838 or FL 8111.																							
CLASSIFICATIE	<table><tr><td>AWS</td><td>A 5.9: ER316L</td></tr><tr><td>EN ISO</td><td>14343-A: S 19 12 3 L</td></tr><tr><td>W.Nr.</td><td>1.4430</td></tr><tr><td>F-nr</td><td>6</td></tr><tr><td>FM</td><td>5</td></tr></table>								AWS	A 5.9: ER316L	EN ISO	14343-A: S 19 12 3 L	W.Nr.	1.4430	F-nr	6	FM	5						
AWS	A 5.9: ER316L																							
EN ISO	14343-A: S 19 12 3 L																							
W.Nr.	1.4430																							
F-nr	6																							
FM	5																							
GESCHIKT VOOR	1.4583, 1.4435, 1.4436, 1.4404, 1.4406, 1.4408, 1.4401, 1.4571, 1.4580, 1.4406, 4.4430 X102CrNiMoNb 18 12, X2CrNiMo 18 14 3 (TP), X4CrNiMo 17 13 3, X2CrNiMo 17 12 2 (TP), X 5CrNiMo 19 11 2, X4CrNiMo 17 12 2 (TP), X6CrNiMo 17 12 2, X6CrNiMoNb 17 12 3, X2CrNiMoN 17 12 3 (TP) 316Cb, 316L, 316L, 316LN, 316H, 316, 316Ti, 316Cb, 316LN UNS S31640, UNS S31603, UNS S31653, UNS S31600, UNS S31635																							
GOEDKEURINGEN	CE																							
LASPOSITIONS	PA PB PC																							
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table><tr><td>C</td><td>Si</td><td>Mn</td><td>P</td><td>S</td><td>Cr</td><td>Ni</td><td>Mo</td></tr><tr><td>0.02</td><td>0.5</td><td>2</td><td>0.02</td><td>0.02</td><td>19</td><td>12</td><td>2.5</td></tr></table>								C	Si	Mn	P	S	Cr	Ni	Mo	0.02	0.5	2	0.02	0.02	19	12	2.5
C	Si	Mn	P	S	Cr	Ni	Mo																	
0.02	0.5	2	0.02	0.02	19	12	2.5																	
MECHANISCHE WAARDEN	<table><thead><tr><th rowspan="2">Heat Treatment</th><th rowspan="2">R_{P0,2} (MPa)</th><th rowspan="2">R_m (MPa)</th><th rowspan="2">A5 (%)</th><th colspan="2">Impact Energy (J) ISO-V</th><th rowspan="2">Hardness</th></tr><tr><th>RT</th><th>-196°C</th></tr></thead><tbody><tr><td>As Welded</td><td>370</td><td>550</td><td>35</td><td>120</td><td>55</td><td>HRc</td></tr></tbody></table>								Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Impact Energy (J) ISO-V		Hardness	RT	-196°C	As Welded	370	550	35	120	55	HRc
Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Impact Energy (J) ISO-V		Hardness																		
				RT	-196°C																			
As Welded	370	550	35	120	55	HRc																		
HERDROGEN	Not required																							
GAS ACC. EN ISO 14175																								



CEWELD SA 316L

SA 316L 2,4MM

Packaging	KG/unit	EanCode
K-415	25	8720663414281

SA 316L 3,2MM

Packaging	KG/unit	EanCode
K-415	25	8720663414298