

CEWELD CuNi10Fe Tig

TYPE Copper-Nickel alloyed TIG welding wire

TOEPASSINGEN The CEWELD® CuNi10Fe Tig is suitable for welding and cladding CuNi-Materials of ISO 17664 and seawater resistant CuZn alloys of ISO 17660 table 3. And also suitable for surfacing on low alloyed and unalloyed steels and grey cast iron.

EIGENSCHAPPEN Sound, pore free deposits on ferrous and non-ferrous base materials.

CLASSIFICATIE EN ISO 24373: Cu 7061 / CuNi10
W.Nr. 2.0873
F-nr 37

GESCHIKT VOOR Cunifer 10, cuni10fe, seawater resistant, marine applications, tubes, pump building, offshore etc.

GOEDKEURINGEN

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)


C	Si	Mn	P	S	Ti	Fe	Cu	Pb	Ni+Co
0.02	0.1	1.1	0.01	0.01	0.4	1.5	Rem.	0.01	10

MECHANISCHE WAARDEN

Heat Treatment	Rp0,2 (MPa)	Rm (MPa)	A5 (%)	Impact Energy (J) ISO-V		Hardness
				RT		
As Welded		300	34	190		80 HB

HERDROGEN Not required

GAS ACC. EN ISO 14175 I1, I3



CEWELD CuNi10Fe Tig

CUNI10FE TIG 1,6 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663409485
CUNI10FE TIG 2,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663409492
CUNI10FE TIG 2,4 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663409508
CUNI10FE TIG 3,2 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663409515