



CEWELD NiCr 52

TYPE	Solid nickel base welding wire for Mig (GMAW) welding.																									
TOEPASSINGEN	CEWELD Nicro 52 filler metal is used for welding nickel-chromium-iron (Inconel 690) alloys to themselves, and for dissimilar welding between nickel-chromium-iron alloys and steels or stainless steels. The applications include surfacing as well as clad-side welding. Interpass temperature of 150°C should be respected,																									
EIGENSCHAPPEN	Excellent resistance against oxidizing media combined with high mechanical strength at room temperature but also at extreme high temperatures combined with high ductility due to the high chromium content. Alloy 690 was developed to offer greater resistance to stress corrosion in the nuclear industry, pure water environment..																									
CLASSIFICATIE	AWS	A 5.14: ERNiCrFe-7																								
	EN ISO	18274: S Ni 6052(NiCr30Fe9)																								
	W.Nr.	2.4642																								
	F-nr	43																								
	FM	6																								
GESCHIKT VOOR	Inconel 690, VDM Alloy 690, Nicrofer 6030 N, FM 52, 2.4642, NiCr29Fe																									
GOEDKEURINGEN																										
LASPOSITIES																										
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Nb</th> <th>Ti</th> <th>Fe</th> </tr> </thead> <tbody> <tr> <td>0.03</td> <td>0.4</td> <td>0.8</td> <td>29.5</td> <td>60</td> <td>0.4</td> <td>0.02</td> <td>0.5</td> <td>9</td> </tr> </tbody> </table>								C	Si	Mn	Cr	Ni	Mo	Nb	Ti	Fe	0.03	0.4	0.8	29.5	60	0.4	0.02	0.5	9
C	Si	Mn	Cr	Ni	Mo	Nb	Ti	Fe																		
0.03	0.4	0.8	29.5	60	0.4	0.02	0.5	9																		
MECHANISCHE WAARDEN	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>Heat Treatment</th> <th>R_{P0,2} (MPa)</th> <th>R_m (MPa)</th> <th>A₅ (%)</th> <th>Hardness</th> </tr> </thead> <tbody> <tr> <td>580°C±15°C 1h</td> <td>260</td> <td>580</td> <td>30</td> <td>200 HB</td> </tr> <tr> <td>As Welded</td> <td>770</td> <td>870</td> <td>16</td> <td>HRc</td> </tr> </tbody> </table>		Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness	580°C±15°C 1h	260	580	30	200 HB	As Welded	770	870	16	HRc									
Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness																						
580°C±15°C 1h	260	580	30	200 HB																						
As Welded	770	870	16	HRc																						
HERDROGEN	Not required																									
GAS ACC. EN ISO 14175	I1																									



CEWELD NiCro 52

NICRO 52 1,14MM

Packaging	KG/unit	EanCode
BS-300	15	8720663418234